



# QCA GREASE MX9

Codes: QCAG00045, QCAG020

Issue: October 2011

Penrite QCA Grease MX9 is an advanced technology, mixed-complex grease, containing 9% solids that provide additional lubrication in high load applications in industries such as **Quarries, Construction and Agriculture.**

It is made using a lithium-calcium complex soap with "built-in" extreme pressure and anti-wear properties. These are further enhanced by the addition of anti-oxidant and corrosion inhibitors. It also uses special tackifiers help the product stay in place and adhere to critical surfaces where it can better lubricate metal surfaces. This is a far better outcome than for some of the "super-stringy" greases that are good at sticking to themselves but require the equipment to work harder to overcome internal friction.

## Application

Penrite QCA Grease MX9 is recommended for use in severe heavy duty applications where high shock loads are common including those in corrosive environments. These include in industrial plants and off-highway equipment used in the mining, agricultural, forestry and construction industries to name a few. Ideal for shackles, bolts, ball joints, king-pins, slow speed bearings and universal joints and may be used as a fifth wheel lubricant.

QCA Grease MX9 is ideal in applications requiring grease with solid anti-wear additives in high temperature environments where conventional lithium greases are unable to be used.

Recommended operating range is -20°C to 140°C.

Not recommended for high speed bearings.

## Customer Benefits

- Minimises squeeze out
- Seals out dirt
- Extremely resistant to water wash out
- High adhesion helps it stay in place
- Prevents scoring and spalling under extreme loads
- Excellent corrosion resistance
- Exceptional load carrying capacity
- STICKS WHERE IT IS NEEDED - NOT TO ITSELF

## Industry Specifications

NLGI 2                  Caterpillar MPGM

## Typical Data

Soap Type	Lithium-Calcium Complex
Base Oil Viscosity, ISO	680
Drop Point, °C	>250
Colour	Grey/Black
Continuous Operating Temperature, °C	-20 to +140
Intermittent Use, °C	>160
Four Ball Weld Load, kg	>800
Appearance	Tacky
Solids Content, %	9



Information in this sheet is based on recent production. Minor variations to typical properties are expected in normal manufacture and do not affect product performance. A MSDS is available on request.

**PENRITE OIL COMPANY PTY LTD**, 88 Lewis Road, Wantirna South Victoria AUSTRALIA 3152, ABN 25 005 001 525

Enquiries: Phone 1300-PENRITE (1300 736 7483)

Fax: 1800-PENRITE (1800 736 7483)

International: Phone: 61 3 9801 0877, Fax: 61 3 9801 0977

**New Zealand** Ph: 0800 533 698, Fax: 0508 736 748

**United Kingdom and EU** Ph: +44 (0) 1594 562357, Fax: +44 (0) 1594 564234

Website: [www.penriteoil.com](http://www.penriteoil.com), Email: [penrite@penriteoil.com](mailto:penrite@penriteoil.com)

**PROUDLY AUSTRALIAN  
FAMILY OWNED  
SINCE 1926**

