



# Product Information

## EURO 25

**Codes:** EURO25005, EURO25020, EURO25060, EURO25205

**Issue:** January 2010

Penrite Euro 25 is a SAE 25W-60 high viscosity, synthetic fortified oil, formulated with additives of the highest standards to ensure protection against wear, corrosion, oil oxidation and sludge under tough Australian Conditions.

Penrite Euro 25 meets the requirements of API CH-4/SJ and ACEA E5.

### APPLICATION

Penrite Euro 25 is designed for use in older European diesel engines operating under high speed/high load/high temperatures, those that are suffering from low pressure, or in engines where oil consumption due to wear has become a problem. It may be used in both naturally aspirated and turbocharged engines. It may also be used in mixed fleets operating under the conditions above.

### CUSTOMER BENEFITS

- Greater engine protection at high operating temperatures.
- Reduced oil consumption due to high operating temperature viscosity (except where consumption is due to bore polishing).
- Modern additive system provides excellent wear and deposit protection
- Improved oil pressure.
- Optimised formulation offers ideal wear, bore polish and deposit protection for older diesel engines.

### INDUSTRY SPECIFICATIONS

Penrite EURO 25 meets the performance requirements of:

API CH-4/SJ	ACEA E5 (Europe)
Mercedes Benz 228.3	MAN 3275
Volvo VDS 2	MTU Type 2
Renault RLD	

## Typical Properties

Density at 15°C, kg/L	0.892
Flash Point, °C	239
Viscosity, Kinematic, cSt	
at 40°C	239
at 100°C	25.0
Viscosity Index	133
Viscosity, Cold Cranking @ -10 °C	5,498
Phosphorus, mass %	0.120

Penrite Oil Company Pty Ltd  
ABN 25 005 001 525  
Ph: 1300 PENRITE (1300 736 748)  
Int: 61 3 980 1 0877  
Email: penrite@penriteoil.com  
[www.penriteoil.com.au](http://www.penriteoil.com.au)

### Environment, Health and Safety

Information is available by request on this product in the Penrite Material Safety Data Sheet. Information in this sheet is based on the most current information available. Minor variations to typical properties not affecting the performance of the product are to be expected in normal manufacture.  
**Issued January 2010**